



SPECIFICATION SHEET

EXPANDABLE POLYSTYRENE (EPS)			
GRADE	K-VALUE	PENTANE CONTENT Wt%	TYPICAL APPLICATION
HS121	55	1.8-2.5	Low Density Block
HS221	55	1-1.8	Medium Density Block
HS321	55	0.7-1	High Density Block, Shaped Packaging
FC422	55	0.5-0.7	Shape Molding. High Density Block
FC522	55	0.3-0.5	Shape Molding. High Density Block
WP526	55	0.3-0.5	Thin-Wall Water Proof Shape Molding. Cup(food contact)