



SPECIFICATION SHEET

Bitumen						
Test	Methodology	30-40	40-50	60-70	85-100	100-120
Density	ASTM D-7	1/01/-1/06	1/01/-1/06	1/01/-1/06	1/01/-1/06	1/01/-1/06
Penetration rate at 25°C	ASTM D-5	30-40	40-50	60-70	85-100	100-120
Softening Point °C	ASTM D-36	55-63	52-60	49-56	45-52	42-49
Ductility at 25°C (cm)	ASTM D-113	100 min	100 Min	100 Min	100 Min	100 Min
FlashPoint	ASTM D-92	250 Min	250 Min	250 Min	250 Min	250 Min
Solubility in Disulfide %wt	ASTM D-4	99/5	99/5	99/5	99/5	99/5
Stain Test	AASHTO T-102	Negative	Negative	Negative	Negative	Negative
Weight Loss by Heating %wt	ASTM D-6	0/2 Max	0/2 Max	0/2 Max	0/2 Max	0/2 Max
Penetration Loss by Heating	ASTM D-6-D-5	20 Max	20 Max	20 Max	20 Max	20 Max