



## SPECIFICATION SHEET

Specification of Petroleum jelly Cosmetic Grade				
No.	CHARACTERISTIC	RESULT	ACCEPTED LIMIT	METHOD
1	Kinematic viscosity at 100 °C	6.2 cSt	6-8 cSt	ASTM D-445
2	Congeeing Point	57.5 °c	54-58 °C	ASTM D-938
3	Penetration Consistency	147 (0.1 mm)	140-160 (0.1 mm)	ASTM D-937
4	Color (Lovibond)	0.7 Y	Max 0.7 Y	IP-17 Method A 2 cell
5	Acidity or Alkalinity	Passed	According to test method	B.P 2007
6	Odor	Passed	Odorless when rubbed on hand	--

ROYAL  
AGRO ENERGY

